

Optical Filters from Photonic Band Gap Air Bridges

Jerry C. Chen, *Student Member, IEEE*, Hermann A. Haus, *Life Fellow, IEEE*, Shanhui Fan,
Pierre R. Villeneuve, and J. D. Joannopoulos

Abstract—Surrounding waveguides by air reduces radiation losses so the air bridge geometry can produce optical filters with sharp transmission resonances and very wide stop bands.

I. INTRODUCTION

IN recent years, photonic band gap materials have attracted much attention. What makes such materials special are wide band gaps or stop bands—ranges of frequencies where no light can propagate. Waves incident on these materials will be reflected if their frequency lies within the gap; the fields decay exponentially inside the material. Possible applications of these unique properties are laser cavities with low thresholds, efficient radiation from planar antennae, and microbends with low loss [1]–[5]. Imperfections in fabrication do not appear to affect these photonic properties significantly [6].

Here we give quantitative description of the filter properties of these structures. For simplicity we study a one dimensional band gap. Conventional gratings may have index modulations of only a few percent. In contrast, photonic band gap materials have large index contrasts typically, as large as of 3:1. This large index ratio or contrast leads to a wide stop band. But as the index contrasts or grating strengths become larger, the fields tend to radiate out of the waveguide. To confine the light, we can surround the waveguide by a lower index material or by a photonic band gap material. In this case, we use air, forming an air bridge (Fig. 1). Since interfaces between air and high dielectric material confine light well, we are able to design an optical filter (Fig. 1) whose transmission resonance peaks at 91%. And since the index contrasts are so large, the stop band width is about 40% of the carrier frequency! We also present a second filter with a very sharp transmission resonance, whose quality factor “ Q ” exceeds 24 000. In this paper, we will first describe how we model these filters, then present more details on the characteristics of these novel filters.

II. METHOD

We calculate the transmission, reflection and radiation spectrum by a finite difference-time domain program. Such programs are reviewed by Miller [7]. Since the index contrasts are so large, analytic methods like coupled mode theory are

Manuscript received October 4, 1995; revised August 9, 1996. This work was supported in part by the MRSEC Program of the NSF under Award DMR 94-00334 and the Army Research Office under Grant DAAH04-93-G-0262.

J. C. Chen is with Bell Laboratories, Lucent Technologies, Holmdel, NJ 07733 USA.

H. A. Haus, S. Fan, P. R. Villeneuve, and J. D. Joannopoulos are with the Research Laboratory of Electronics, Center for Material Science and Engineering, Massachusetts Institute of Technology, Cambridge, MA 02139 USA.

Publisher Item Identifier S 0733-8724(96)08453-8.

not as accurate. We need to turn to numerical techniques. Specifically, we integrate Maxwell’s equations forward in time over the two spatial dimensions:

$$\begin{aligned}\nabla \times E &= -\mu \frac{\partial H}{\partial t} \\ \nabla \times H &= \epsilon \frac{\partial E}{\partial t}.\end{aligned}$$

For accuracy, the electric E and magnetic H fields are separated by half steps in space and time, in a Yee lattice [8]. This initial value problem is explicit; the fields at one time step depend only on the fields at the previous time step. As a result, such schemes can be run efficiently on parallel computers [9].

In such programs, the boundary conditions tend to be the most challenging part. The treatment of the outer boundary (unbounded space) is of particular importance. The popular absorbing boundary condition [10] suffers from reflections from the computational border. These spurious reflections become particularly severe in microstrip line simulations, where the indexes of refraction changes along the border. Over the years, many schemes have been devised to minimize these reflections [11]–[13]. The recently reported Berenger’s perfectly matched layer (PML) [14] gives low reflections, even for microstrip lines [15]. To achieve such low reflections, researchers [14] and [15] increase the conductivity or absorption strength or the matching layers quadratically, with a power of $n = 2$. However, Chen and Li [16] find that significant further improvement can be achieved by using quartic gradations ($n = 4$). Following this example, we choose our layer to be $\delta = 12$ grid points thick, which has a theoretical reflectivity of $R(\theta = 0) = 10^{-6}$ in free space. Inside the dielectric, the conductivity is multiplied by the dielectric constant [15]. These low reflections eliminate the Fabry–Perot fringes that would otherwise arise from the reflections at the grating region and the computational boundary [16].

One can use a sine wave source to calculate the transmission and reflection at one frequency [17]. However, pulsed sources are more efficient for calculations over a range of frequencies. In particular, one can send in a Gaussian source to the filter and monitor the reflected and transmitted pulses. The fast Fourier transform (FFT) of these pulses, normalized to the spectrum of the input pulse, gives the reflection and transmission spectrum. In our simulations, we send in a Gaussian pulse whose pulse width equals the period $1/f$.

$$\sin(2\pi ft) \exp[-(ft - 4)^2], \quad t \geq 0.$$

This gives sufficient frequency range to model the filters.




Fig. 1. (a) Schematic of air-bridge with six circular holes and (b) another bridge with 33 notches.




Fig. 2. Fractional power lost to substrate as a function of substrate index.

We can also obtain physical insight about the transmission peak, by examining the resonator properties. The energy of a resonator decays exponentially.

$$\begin{aligned} W &= W_0 e^{-\omega_0 t/Q} \\ &= W_0 e^{-2t/\tau} \end{aligned}$$

where $Q = \omega_0 \tau / 2$ is the quality factor, ω_0 is the resonance frequency, and τ is the decay constant. Using coupled mode theory, Haus [18] calculated the transmitted power through a resonator

$$T_{pwr} = \frac{4\tau^2}{\frac{\tau_{e1}\tau_{e2}}{(\omega - \omega_0)^2 \tau^2 + 1}}$$

where τ_{e1} measures the decay of fields into the external world or waveguide from port 1. Since our filters have symmetry input and output ports, τ_{e1} and τ_{e2} are equal and can be combined into an overall external decay constant $\tau_e = \tau_{e1}/2$. This simplifies the transmission to

$$T_{pwr} = \frac{\left(\frac{\tau^2}{\tau_e}\right)^2}{(\omega - \omega_0)^2 \tau^2 + 1}$$

This transmission expression considers the input coupling between the waveguide and the resonator, the intrinsic radiation losses of the resonator and the output coupling of power to the waveguide. The maximum transmission is $T_{pwr}(\omega = \omega_0) = (\tau^2/\tau_e)^2 = (Q^2/Q_e)^2$ where Q_e is the external quality factor. The external quality factor measures the rate at which energy is transferred from the resonator cavity to the external waveguides. Specifically, $Q_e = \omega\tau_e/2$ is the number of cycles needed for the resonator energy to decay to $1/e^{2\pi}$. The ratio




Fig. 3. Power transmitted, reflected and radiated as a function of wavelength.

of the resonance frequency and the full width half maximum (FWHM) of this transmission resonance is

$$\begin{aligned} Q_{\text{FWHM}} &= \frac{\omega_0}{\frac{\tau}{2}} \\ &= \frac{\omega_0 \tau}{2} \\ &= Q_{\text{resonator}} \end{aligned}$$

This suggests that from the transmission peak, one can predict such resonator parameters as ω_0 , Q , and Q_e .

We calculate such parameters using the finite difference time domain method. To extract the quality factors, we need




Fig. 4. Top panel: Electric field component lying in the page and transverse to the propagation direction, at transmission resonance. Bottom panel: Magnetic field normal to the page at transmission resonance.

to excite that resonator eigenmode. An arbitrary initial field can be decomposed into many eigenmodes, each of which decays exponentially with a rate ω/Q . A sufficiently long propagation will yield the mode with the largest Q ; the other eigenmodes will be negligibly small [19]. Of course, this calculation can be speeded up if the initial field resembles the high Q eigenmodes. By monitoring the rate of energy decay, we obtain the Q of the eigenmode. The resonance frequency ω_0 comes from the oscillation rate of the electric or magnetic field.

So, by knowing the resonator properties, we can predict some features of the transmission. There is good agreement between the two.

III. RESULTS

The optical filters we wish to investigate are air bridges (Fig. 1). The air surrounding the waveguide on all four sides—top, bottom, left, and right—helps to confine the light inside the bridge waveguide. This suppresses the radiation losses, giving a high Q resonator and a narrow transmission resonance peak. To illustrate this point, let us examine what happens if the air were replaced by another material on just one side. We will perform a 2-D model of an air bridge, by focusing only on its crosssection. The air bridge shown in Fig. 1(a) has six air holes, which are spaced 0.232 free-space wavelengths λ or (for $\lambda = 1.55 \mu\text{m}$) $0.360 \mu\text{m}$ apart. This hole-to-hole separation increases to 0.325λ or $0.503 \mu\text{m}$ for the center two holes, giving rise to the quarter wave-

like phase shift that gives the transmission resonance. The diameter of each hole is 0.167λ or $0.258 \mu\text{m}$. The entire structure is only 1.420λ or $2.20 \mu\text{m}$. This small size allows for a compact integration of many wavelength filters on a small chip. A slightly longer version of this structure—one with more air holes—can act as a high Q microcavity [17], [19], and [20]. Others have constructed microcavities using whispering gallery modes [21]. Our waveguide has a rather narrow width 0.281λ or $0.435 \mu\text{m}$, so they are very difficult to couple into. In practice, an adiabatic taper would be needed to improve coupling efficiency. We choose the core index to be $n = 3.4$ because it is close to the indexes for GaAs and Si. Now, if we place AIAs next to the waveguide, about 80% is radiated into the AIAs slab. So, even an index contrast of $3.4:2.8$ is not enough to confine the light (Fig. 2). The radiation loss drops dramatically as the index becomes lower. For air ($n = 1$) the loss to that one side becomes almost negligible. For more details on how this calculation is performed, see [17].

Fig. 3 plots the transmitted and reflected power as a function of wavelength. Notice the reflection is almost unity over a 600 nm range. This is about 40% of the carrier wavelength! The Q or ratio of the carrier wavelength to the transmission FWHM is 264.7. The radiation loss is near 0, over most of the range. At lower wavelengths, however, radiation increases as light is coupled to higher order transverse modes. Fig. 4 shows the electric field (pointing down) and the magnetic field (pointing out of page) at transmission resonance. Coming in from the




Fig. 5. Top panel: Absolute value of electric field normal to page, at transmission resonance. Bottom panel: Absolute value of magnetic field lying in the page and transverse to the propagation direction, at transmission resonance.

left side of the figure, light is coupled to the resonator mode in which most of the light is localized about the so-called quarter wave phase shift or dielectric defect. Then over 91% is transmitted to the other side! This air bridge geometry allows a wide stopband and a large transmission. And most of the light is confined to the waveguide.

By measuring the energy decay of the resonator, we find the quality factor of 269.6. This compares favorably to the $Q = 264.7$ obtained from the transmission width. Since at resonance, the maximum transmitted power is $T_{pwr} = 0.91174$ and $T_{pwr} = (Q/Q_e)^2$, then $Q_e = 1.0473Q = 282.3$. The estimated radiation quality factor is $Q_r = 1/(1/269.6 - 1/282.3) = 5993$, using

$$\frac{1}{Q} = \frac{1}{Q_r} + \frac{1}{Q_e}.$$

We present another filter with an even larger “ Q .” By omitting the holes and by notching the sides of the air-bridge instead [Fig. 1(b)], we reduce the index contrasts or grating strengths. This reduces the stop band width. More importantly, this also lowers the radiation losses. Specifically, the stop band width falls to 70 nm. Note that for optical communication purposes, this width is more than adequate, being about double the gain bandwidth of erbium amplifiers. The quality factor is much larger than before; Q exceeds 20 000. The notches are 0.0356 free-space wavelengths deep and 0.0888 wavelengths long. Notches are separated from each other by 0.178 wavelengths. As before, we choose an index of 3.4 for the bridge. It is 0.195 wavelengths wide and 11.812 wavelengths long. There are 33 notch pairs on each side of the phase slip, which measures 0.178 wavelengths long. Fig. 5 shows the absolute values of the electric field (normal to page) and the magnetic field (in the page but normal to propagation direction). The transmitted, reflected, and radiated powers are shown in Fig. 6. Note the sharpness of the transmission peak at resonance. There are only a few data points in the center of this resonance. Calculating more points would require much




Fig. 6. Fraction of power transmitted, reflected, and radiated by notched filter as a function of frequency.

computer time. From these points, the quality factor must exceed 11 000. From the energy decay, we find a “ Q ” of

24 100. The highest transmitted power observed is 0.741. This corresponds to a radiation “ Q ” of over 173 000! Moving off resonance, the transmission falls by 40 dB. As a result, another filter with a slightly different transmission resonance would see very little crosstalk.

In conclusion, we have presented optical filters based on air bridge geometries. The suppression of radiation leads a large transmissions. The large index modulations give enormous stop bands whose widths are about 40% of the carrier wavelength. We can also achieve “ Q ”s of over 24 000, resulting in very sharp transmission resonances.

ACKNOWLEDGMENT

J. C. Chen would like to thank Dr. K. Li and Dr. R. Shin for use of their FDTD code with PML boundaries. These simulations ran on the NSF San Diego Supercomputer Center’s Cray C90. J. C. Chen enjoyed discussions with K. Y. Lim and P. S. Martin about fabrication issues.

REFERENCES

- [1] E. Yablonovitch, “Photonic band-gap structures,” *J. Opt. Soc. Amer. B*, vol. 10, pp. 283–295, Feb. 1993.
- [2] J. W. Haus, “A brief review of theoretical results for photonic band structure,” *J. Mod. Optics*, vol. 41, no. 2, pp. 195–207, 1994.
- [3] R. D. Meade, A. Devenyi, J. D. Joannopoulos, O. L. Altherhand, D. A. Smith, and K. Kash, “Novel applications of photonic band gap materials: Low loss bends and high Q cavities,” *J. Appl. Phys.*, vol. 75, p. 4753, May 1994.
- [4] P. R. Villeneuve and M. Piché, “Photonic bandgaps in periodic dielectric structures,” *Prog. Quantum Electron.*, vol. 18, no. 2, pp. 153–200, 1994.
- [5] J. D. Joannopoulos, R. D. Meade, and J. N. Winn, *Photonic Crystals: Molding the Flow of Light*. Princeton, NJ: Princeton University Press, 1995.
- [6] S. Fan, P. R. Villeneuve, and J. D. Joannopoulos, “Theoretical investigation of fabrication-related disorder on the properties of photonic crystals,” *J. Appl. Phys.*, vol. 78, pp. 1415–1418, Aug. 1, 1995.
- [7] E. K. Miller, “Time-domain modeling in electromagnetics,” *J. Electromag. Waves Appl.*, vol. 8, pp. 1125–1172, Sept. 1994.
- [8] K. S. Yee, “Numerical solution of initial boundary value problems involving Maxwell’s equations in isotropic media,” *IEEE Trans. Antennas Propagat.*, vol. AP-14, pp. 302–307, May 1966.
- [9] J. C. Chen, “A parallel approach for modeling optical waveguides,” in *Proc. 1994 MIT Student Workshop on Scalable Computing*, Cape Cod, MA, July 21–22, 1994, Paper 17.
- [10] B. Engquist and A. Majda, “Absorbing boundary conditions for the numerical simulation of waves,” *Math. Computat.*, vol. 31, no. 139, pp. 629–651, 1977.
- [11] Z. Bi, K. Wu, C. Wu, and J. Litva, “A dispersive boundary condition for microstrip component analysis using the FD-TD method,” *IEEE Trans. Microwave Theory Tech.*, vol. 40, pp. 774–777, Apr. 1992.
- [12] C. J. Raiton, E. M. Daniel, D.-L. Paul, and J. P. McGeehan, “Optimized absorbing boundary conditions for the analysis of planar circuits using the finite difference time domain method,” *IEEE Trans. Microwave Theory Tech.*, vol. 41, pp. 290–297, Feb. 1993.
- [13] K. Naishadham and X. P. Lin, “Application of spectral domain Prony’s method to the FDTD analysis of planar microstrip circuits,” *IEEE Trans. Microwave Theory Tech.*, vol. 42, pp. 2391–2398, Dec. 1994.
- [14] J.-P. Berenger, “A perfectly matched layer for the absorption of electromagnetic waves,” *J. Computat. Phys.*, vol. 114, pp. 185–200, Oct. 1994.
- [15] C. E. Reuter, R. M. Joseph, E. T. Thiele, D. S. Katz, and A. Taflove, “Ultrawideband absorbing boundary condition for termination of waveguiding structures in FD-TD simulations,” *IEEE Microwave Guided Wave Lett.*, vol. 4, pp. 344–346, Oct. 1994.
- [16] J. C. Chen and K. Li, “Quartic perfectly matched layers for dielectric waveguides and gratings,” *Microwave Opt. Tech. Lett.*, Dec. 20, 1995.
- [17] J. C. Chen, H. A. Haus, J. N. Winn, S. Fan, and J. D. Joannopoulos, “Wide stop band optical filters from photonic band gap air bridges,” in *Guided Wave Optoelectronics: Device Characterization, Analysis and Design*, T. Tamir, H. Bertoni, and G. Griffel, Eds. New York: Plenum, 1995, pp. 477–483.
- [18] H. A. Haus, “Distributed feedback structures,” in *Waves and Fields in Optoelectronics*. Englewood Cliffs, NJ: Prentice-Hall, 1984.
- [19] S. Fan, J. N. Winn, A. Devenyi, J. C. Chen, R. D. Meade, and J. D. Joannopoulos, “Guided and defect modes in periodic dielectric waveguides,” *J. Opt. Soc. Amer. B*, vol. 12, pp. 1267–1272, July 1995.
- [20] P. R. Villeneuve, S. Fan, J. D. Joannopoulos, K. Y. Lim, G. S. Petrich, L. A. Kolodziejski, and L. R. Reif, “Air-bridge microcavity,” *Appl. Phys. Lett.*, vol. 67, pp. 167–169, July 1995.
- [21] S. L. McCall, A. F. J. Levi, R. E. Slusher, S. J. Pearton, and R. A. Logan, “Whispering-gallery mode microdisk lasers,” *Appl. Phys. Lett.*, vol. 60, pp. 289–291, Jan. 20, 1992.



Jerry C. Chen (S’88) was born in Troy, NY, on August 8, 1967. He graduated highest honors with the B.S.E. degree in electrical engineering and a certificate in engineering physics from Princeton University, Princeton, NJ, in 1989. From 1989 to 1992, he was an Office of Naval Research Fellow where he received the S.M. degree in electrical engineering from Massachusetts Institute of Technology (M.I.T.), Cambridge in 1991. He is currently pursuing the Ph.D. degree in electrical engineering at M.I.T. His master’s thesis under Prof. E. P. Ippen

involved both theoretical and experimental work on femtosecond lasers.

Along with his Ph.D. Advisors Prof. H. A. Haus and Prof. J. D. Joannopoulos, he has studied optical filters, waveguide eigenmodes, and photonic bandgaps. Currently, he is with Bell Laboratories, Lucent Technologies, Holmdel, NJ, working on the design of wavelength grating routers.

Mr. Chen is a member of the Optical Society of America, Photonics Society of Chinese-Americans, Phi Beta Kappa, Sigma Xi, and Tau Beta Pi.



Hermann A. Haus (S’50–A’55–SM’58–F’62–LF’91) was born in Ljubljana, Slovenia, in 1925. He attended the Technische Hochschule, Graz, and the Technische Hochschule, Vienna, Austria. He received the B.Sc. degree from Union College, Schenectady, NY, in 1949, the M.S. degree from Rensselaer Polytechnic Institute, Troy, NY, in 1951, and the Sc.D. degree from the Massachusetts Institute of Technology (M.I.T.), Cambridge in 1954.

He joined the Faculty of Electrical Engineering at M.I.T. in 1954, where he is an Institute Professor. He is engaged in research in electromagnetic theory and lasers. He is the author or coauthor of five books and more than 260 journal articles.

Dr. Haus is a member of Sigma Xi, Eta Kappa Nu, Tau Beta Pi, the American Physical Society, the National Academy of Engineering, the National Academy of Sciences, and a Fellow of the American Academy of Arts and Sciences. He is the recipient of the 1984 Award of the IEEE Quantum Electronics and Applications Society, the 1987 Charles Hard Townes Prize of the Optical Society of America, the 1990 Outstanding Paper Award of the IEEE TRANSACTIONS ON EDUCATION, the 1991 IEEE Education Medal of the Institute of Electrical and Electronics Engineers, the 1994 Frederic Ives Medal of the Optical Society of America, and the President’s 1995 National Science Medal. He holds honorary doctor’s degrees from Union College, Schenectady, New York, the Technical University of Vienna, Austria, and the University of Ghent, Belgium.

Shanhui Fan was born in Zhengzhou, China, in 1972. He was an undergraduate at the University of Science and Technology of China from 1988 to 1992. He is currently pursuing the Ph.D. degree in the Department of Physics at Massachusetts Institute of Technology, Cambridge graduating in June 1997.

Since 1993, he has been in Prof. J. D. Joannopoulos’ group working on theory and device applications of photonic crystals. He holds three U.S. patents and has authored 10 journal papers on photonic crystals.

Mr. Fan is a member of the American Physical Society.

Pierre R. Villeneuve was born in Hull, P.Q., Canada, in 1966. He received the B.Sc. degree from the University of Ottawa in 1988, and the M.Sc. and Ph.D. degrees from Université Laval, Québec City, in 1990 and 1993, respectively.

In 1993, he was awarded a postdoctoral fellowship from the Canadian government which he held at the Massachusetts Institute of Technology (M.I.T.), Cambridge. He was appointed Research Scientist in 1996 at the Research Laboratory of Electronics at M.I.T. He is engaged in research in electromagnetic theory and quantum optics. He has been investigating the properties of photonic bandgap materials and their applications to the design of integrated photonic devices and semiconductor lasers. He is the author or coauthor of 30 publications and three U.S. patents. In addition to his appointment at M.I.T., he will be teaching, in 1997, a course on lasers and electro-optics at Brown University, Providence, RI.

Dr. Villeneuve is a member of the Optical Society of America and the American Physical Society.

John D. Joannopoulos was born in New York, NY, on April 26, 1947. He received the B.A. and Ph.D. degrees from the University of California, Berkeley in 1968 and 1974, respectively.

He joined the Faculty of Physics at the Massachusetts Institute of Technology, Cambridge in 1974. His research interests have been in theoretical condensed matter physics and he is responsible for the development of numerous calculational schemes and techniques for the study of complex solid systems. His interests span a wide range of topics including the electronic and vibrational structure of crystalline and amorphous bulk solids, their surfaces, interfaces, and defects; localization in disordered systems; phase transitions and critical phenomena; and most recently, the theory of photonic bandgap crystals. He is the author or coauthor of more than 275 journal articles and one textbook and holds six U.S. patents.

Dr. Joannopoulos is a member of the American Association for the Advancement of Science, the Materials Research Society, and a Fellow of the American Physical Society. He is the recipient of the 1991 School of Science Graduate Teaching Award, the 1996 William Buechner Teaching Prize, and the 1997 David Adler Award. He is a Divisional Associate Editor of *Physical Review Letters*, and Member of the Editorial Board of *Reviews of Modern Physics*.